

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106


1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400

## TEST REPORT

**Client :** Inspired Floorcoverings  
Level 1, Suite 3, 72 Terrigal Esplanade  
Terrigal NSW 2260

**Test Number :** 24-004350  
**Issue Date :** 10/12/2024  
**Print Date :** 10/12/2024

**Sample Description** Clients Ref : "Stonewall"  
Loop pile carpet plank  
End Use : Flooring  
Nominal Composition : Nylon, glass layer, PVC  
Nominal Mass per Unit Area/Density : 700g/m<sup>2</sup>  
Nominal Thickness : 7-8mm



338023

73821

Page 1 of 3

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing  
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400

## TEST REPORT

**Client :** Inspired Floorcoverings  
Level 1, Suite 3, 72 Terrigal Esplanade  
Terrigal NSW 2260

**Test Number :** 24-004350  
**Issue Date :** 10/12/2024  
**Print Date :** 10/12/2024

### AS ISO 9239.1-2003

### Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 31-10-2024

Date Tested 10-12-2024

CHF Value	1	2	3	Mean
Length	5.8	5.6	5.8	5.7 kW/m <sup>2</sup>
Width	7.4	-	-	- kW/m <sup>2</sup>
HF-30 Value	1	2	3	Mean
Length	6.0	5.8	6.4	6.1 kW/m <sup>2</sup>
Width	-	-	-	- kW/m <sup>2</sup>
Smoke Value	1	2	3	Mean
Length	197	119	184	167 % .min
Width	142	-	-	- % .min

338023

73821

Page 2 of 3

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing  
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400

## TEST REPORT

**Client :** Inspired Floorcoverings  
Level 1, Suite 3, 72 Terrigal Esplanade  
Terrigal NSW 2260

**Test Number :** 24-004350  
**Issue Date :** 10/12/2024  
**Print Date :** 10/12/2024

### Observations:

Melting

Yes

HF30 not reported as flame out time occurred before 30 minutes.

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of  $23\pm 2^{\circ}\text{C}$  and relative humidity of  $50\pm 5\%$  for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

338023

73821

Page 3 of 3

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing  
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR